

ELEMENTIS
SPECIALTIES

净味环保型及功能性建筑涂料
助剂最新进展与配方优化

Walee Wang / 王全义
Technical Service Manager
Elementis Specialties
海名斯特殊化学
One-stop Total Solution Provider
—一站式整体解决方案的伙伴

DEUCHEM
SPECIALTIES
海名斯·德谦

2009/1/12

分水？热稳定性弱？

原因：
A: PVC较高？
B: 流变助剂搭配不合理？
C: 体系低剪粘度较低？较弱的防沉性？体系对温度较敏感

DEUCHEM
SPECIALTIES
海名斯·德谦

One-stop Total Solution Provider
—一站式整体解决方案的伙伴

2009/1/12

早期耐水性较弱？

原因：
A: 乳液？流变助剂搭配不合理？
B: 表面活性剂的选择？

DEUCHEM
SPECIALTIES
海名斯·德谦

One-stop Total Solution Provider
—一站式整体解决方案的伙伴

2009/1/12

抗飞溅性差？

原因：
A: 流变助剂搭配不合理？

DEUCHEM
SPECIALTIES
海名斯·德谦

One-stop Total Solution Provider
—一站式整体解决方案的伙伴

2009/1/12

浮色发花？展色性弱？

原因：
基料？
A: 润湿？分散？
B: 流变助剂？

色浆？
A: 润湿剂的选择？

DEUCHEM
SPECIALTIES
海名斯·德谦

One-stop Total Solution Provider
—一站式整体解决方案的伙伴

2009/1/12

NUOSPERSE®

Wetting and Dispersing Agents /
润湿分散剂

RHEOLATE®
BENTONE®
THIXATROL®
NUOSPERSE®
RHEOX®
DAPRO®
TINT-AYD®

DEUCHEM
SPECIALTIES
海名斯·德谦

One-stop Total Solution Provider
—一站式整体解决方案的伙伴

2009/1/12

Dispersing and Wetting Agents

ELEMENTIS SURFACTANTS

Dispersing agents/分散剂

- Dispersing agents are additives that provide optimal stability of pigment particles by **charge** and/or **steric** stabilization/通过空间位阻或电荷稳定颜填料

Wetting agents/润湿剂

- Wetting agents reduce the interfacial tension and improve **pigment surface wetting**/降低表面张力，提高表面润湿

(Many surfactants function as both)

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

润湿分散机理

ELEMENTIS SURFACTANTS

Step 1:
Agglomerates/
附聚体

Step 2:
Wetting Agent/润湿剂
初级粒子

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

Stabilisation/稳定性机理

ELEMENTIS SURFACTANTS

- 电荷稳定
- 空间位阻

Anionics Polymeric
Only in polar medium -like water

Nonionics Polymeric

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

分散剂测试- 乳胶漆

ELEMENTIS SURFACTANTS

Pigment dispersant demand curve/分散剂需求量测试 **NUOSPERSE® FX 605**

NUOSPERSE® FX 504 优异的储存稳定性

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

Stability Test at 60°C/稳定性测试

ELEMENTIS SURFACTANTS

FX 605 DIBMA

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

NUOSPERSE® FN 265 润湿剂

ELEMENTIS SURFACTANTS

Alkyl Phenol Ethoxylate
- HLB Value = 13 - 14

NUOSPERSE FN 265
- Modified Alkyl Ethoxylate
- APE free

Pigment

Charge transfer interactions: physical adsorption

• Wetting
• Steric stabilization

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

NUOSPERE® FN 265

ELEMENTIS
SPECIALIST IN SURFACTANTS

- 特征
 - 90%，不含APE 非离子型润湿剂
 - 有效降低表面张力，低起泡性能；
- 优点
 - 为疏水及亲水型颜填料提供良好的润湿，优异的展色性能及色浆相容性
 - 提高涂料的储存稳定性
 - 降低消泡剂的用量
 - NO-VOC

competitor / NUOSPERE® FN 265 / Nonylphenol 10EO
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

良好的低温稳定性

ELEMENTIS
SPECIALIST IN SURFACTANTS

Competitor NUOSPERE FN 265 Competitor NUOSPERE FN 265 Competitor NUOSPERE FN 265
75 °F / 23 °C 60 °F / 16 °C 40 °F / 4 °C

DEUCHEM
SPECIALISTS IN SURFACTANTS
海名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

Wetting problem / 润湿问题
Colour Development Test: Dispersion paint.

ELEMENTIS
SPECIALIST IN SURFACTANTS

问题: 2 Min Red Devil 10 Min

解决方案: Add 0.5% NUOSPERE FN 265
2 Min Red Devil 10 Min

DEUCHEM
SPECIALISTS IN SURFACTANTS
海名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

怎样解决色浆相容性问题

ELEMENTIS
SPECIALIST IN SURFACTANTS

- Selecting a **nonionic** additive with the proper HLB to improve wetting (additive should have similar HLB to the paint system) /选择非离子表面活性剂提高基料润湿
- Selecting the proper, mostly **anionic**, **hydrophilic** surfactant for universal colorants and more hydrophobic **anionic** surfactant for non-polar colorants to improve dispersion/选择阴离子型表面活性剂，提高展色性能

DEUCHEM
SPECIALISTS IN SURFACTANTS
海名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE®
BENTONE®
THIXATROL®
NUOSPERE®
RHEOX®
DAPRO®
TINT-AYD®

ELEMENTIS
SPECIALIST IN SURFACTANTS

水性体系用流变助剂

One-stop Total Solution Provider
一站式整体解决方案的伙伴


Why use rheological additives ?

ELEMENTIS
SPECIALIST IN SURFACTANTS



- Sag – control/抗流挂
- Anti – settling/防沉
- Spatter – resistance/抗飞溅
- Easy application/易添加
- Levelling...../流平



DEUCHEM
SPECIALISTS IN SURFACTANTS
海名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴



- ### 水性流变助剂的分类
- ELEMENTIS
SPECIALTIES
- 纤维素类 (HEC)
 - 锂蒙脱石/蒙脱石类(Clay based)
 - 丙烯酸碱溶胀型 (ASE)
 - 疏水改性丙烯酸碱溶胀型 (HASE)
 - 聚氨酯缔合型(PEUPU)
 - 聚醚聚氨酯类缔合型(PEPO)
- DEUCHEM
德名斯·健康
2009/1/12
- One-stop Total Solution Provider
一站式整体解决方案的伙伴





锂蒙脱石类流变助剂


Ease of Dispersion/易分散性



	BENTONE® EW	BENTONE® DE
Milling Time (mins)	4% pregel	14% pregel
2	65 μm	12 μm
5	65 μm	12 μm
20	50 μm	12 μm
40	30 μm	12 μm
60	25 μm	12 μm

Dispermat 40mm @ 3000rpm

DEUCHEM
海名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴





RHEOLATE 150

PHYSICAL PROPERTIES/物理性能

Composition/组成	Acrylic emulsion /丙烯酸乳液
Appearance/外观	Milky white/奶白色
Non-volatile content/不挥发份	28.5-31.5%
Solvent/溶剂组成	Water/水

APE Free, VOC Free

DEUCHEM DEUTSCHE CHEMIE
德名斯·德康
2009/1/22

One-stop Total Solution Provider 一站式整体解决方案的伙伴

RHEOLATE 150

KEY PROPERTIES/主要性能

- Excellent dilutability/优异的稳定性
- To provide high viscosity in low shear rate./提供低剪切粘度
- Efficient develops package viscosity/有效包装粘度
- Reduces spattering during roller application/抗飞溅
- Provides excellent sag and anti-settling resistance/抗流挂与防沉
- Liquid form and low viscosity - easy incorporated/易添加
- APEO (alkyl phenol ethoxylate) free and solvent free./不含APEO 和溶剂
- Good compatibility with generally water borne resin /同水性树脂有良好的相容性
- Reduces syneresis./抗分水

DEUCHEM
海名斯·德谦
One-stop Total Solution Provider
一站式整体解决方案的伙伴
2009/6/22

RHEOLATE 150

Application: 75%PVC 内墙涂料 -100KU

RHEOLATE 150 : RHEOLATE 278=1:1

System 2: 75% PVC interior wall paint system based on styrene acrylic emulsion
Initial Stomer viscosity: 100KU

Results	RHEOLATE® 150 / RHEOLATE 278	HEC 20000 / RHEOLATE 278	HEC 30000 / RHEOLATE 278	HEC 25000 / RHEOLATE 278	RHEOLATE® 150 / RHEOLATE 278	HEC 25000 / RHEOLATE 278
Loading Test	1.15	0.46	0.41	0.1/0.22	0.5/0.6	1.25/1.3
Stomer Viscosity, KU	111.6	108.8	108.1	108.1	103.4	109
Brookfield viscosity, CPS (20°C open, 100 rpm)	23000/ 4000	18000/ 3900/ 21900/ 4470	18000/ 3900	19000/ 3700	6040/ 2200	1940/ 2200
ID viscosity, P	0.89	1.10	1.10	0.83	1.11	0.84
Levelling property	○	×	○	●	●	○
Flow Property	●	●	●	●	●	●
Color development	○	○	●	○	○	○
Storage stability, aging test (20 weeks)	○	○	○	○	○	○
Spatter resistance	●	●	●	●	●	●
Dimensional resistance	○	●	●	○	○	●

Legend: ○ Excellent ● Good ✕ Poor

DEUCHEM
海名斯·德谦
One-stop Total Solution Provider
一站式整体解决方案的伙伴
2009/6/22

RHEOLATE 150

Application:40%PVC 外墙涂料体系 -100KU

System 3: 40%PVC Exterior Wall Paint system based on pure acrylic emulsion
Initial Stomer viscosity: 100-105KU

Results	RHEOLATE® 150 / RHEOLATE 278	RHEOLATE® 150 / RHEOLATE 212	HE C30000 / RHEOLATE 278	HEC 25000 / RHEOLATE 278
Loading Test	0.22/0.26	0.45/0.4	0.1/0.32	0.1/0.29
Stomer viscosity, KU	110.3	116.6	112.6	115.9
Brookfield viscosity, CPS (20°C open, 100 rpm)	9160/ 3404	15802/ 4980	14442/ 4630	15720/ 4620
ID viscosity, P	0.805	1.1	0.875	0.932
Levelling property	○	○	●	●
Flow Property	○	○	●	●
Color development	○	○	○	○
Storage stability, aging test (20 weeks)	○	○	○	○
Dimensional resistance	○	○	●	●

Legend: ○ Excellent ● Good ✕ Poor

DEUCHEM
海名斯·德谦
One-stop Total Solution Provider
一站式整体解决方案的伙伴
2009/6/22

RHEOLATE 150

Comparison of dilution stability in 75% PVC Styrene Acrylic Interior Wall Paint based on 998A

Dilution	RHEOLATE 150 (KU)	HEC 30000 (KU)	HEC 25000 (KU)
Control	~100	~100	~100
5% dilution	~95	~85	~75
10% dilution	~98	~80	~70
15% dilution	~100	~75	~65
20% dilution	~95	~70	~60

DEUCHEM
海名斯·德谦
One-stop Total Solution Provider
一站式整体解决方案的伙伴
2009/6/22

RHEOLATE 150 Versus HEC

75% PVC emulsion system

DEUCHEM
海名斯·德谦
One-stop Total Solution Provider
一站式整体解决方案的伙伴
2009/6/22

RHEOLATE 150 Versus HEC

75% PVC BATF RS-998A 苯丙乳液内墙涂料中
Spatter Resistance Test/抗飞溅测试

Sample	R-150	HEC 2	HEC 3
Image			

DEUCHEM
海名斯·德谦
One-stop Total Solution Provider
一站式整体解决方案的伙伴
2009/6/22

RHEOLATE 150

Storage stability test/储存稳定性
(50oC after 7 days)

Reduced syneresis/降低分水

DEUCHEM
SOLVENTES & RESINS
海名斯·德康
2009/6/22

ELEMENTIS
SOLVATIVES

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE 150 Versus HEC

75% PVC emulsion system, Leveling Test

	RHEOALTE 150	HEC 2
Initial	Smooth	Smooth
After 24 hours	Smooth	Smooth

DEUCHEM
SOLVENTES & RESINS
海名斯·德康
2009/6/22

ELEMENTIS
SOLVATIVES

One-stop Total Solution Provider
一站式整体解决方案的伙伴

Formula 2: 40%PVC Exterior Wall Paint

Stormer Viscosity@KU, in 40%PVC exterior wall paint system

Formulation	Initial (KU)	2 weeks aging test (KU)
R-150/R278	105	135
R-150R-212	105	135
R-425R-278	105	135
HEC2/R-278	105	135
HEC3/R-278	105	135
HEC5/R-278	105	135

Initial,25°C ■ Stormer viscosity, KU □ Stormer viscosity, KU, 2 weeks aging test

DEUCHEM
SOLVENTES & RESINS
海名斯·德康
2009/12

ELEMENTIS
SOLVATIVES

One-stop Total Solution Provider
一站式整体解决方案的伙伴

Formula 2: 40%PVC Exterior Wall Paint

Chart 2: Brookfield Viscosity,CPs

Brookfield Viscosity@CPs,overnight,in 40% PVC exterior wall paint system

RPM	R-150/R278	R-150R-212	R-425R-278	HEC2/R-278	HEC3/R-278	HEC5/R-278
10 rpm	15000	15000	15000	15000	15000	15000
20 rpm	8000	8000	8000	8000	8000	8000
50 rpm	4000	4000	4000	4000	4000	4000
100 rpm	2000	2000	2000	2000	2000	2000

Brookfield Viscosity@CPs,overnight,in 40% PVC exterior wall paint system

DEUCHEM
SOLVENTES & RESINS
海名斯·德康
2009/12

ELEMENTIS
SOLVATIVES

One-stop Total Solution Provider
一站式整体解决方案的伙伴

Formula 3: Flexible Texture Coatings

RHEOLATE 150 & BENAQUA 4000

Application by foaming
Roller(1-poor,5-mm gap)
Spindle # 5
6 rpm 51196
12 rpm 34830
30 rpm 20560
60 rpm 13960
1.1 3.67

DEUCHEM
SOLVENTES & RESINS
海名斯·德康
2009/12

ELEMENTIS
SOLVATIVES

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE 150 VS ASE

Stormer viscosity,KU, in 75% PVC interior wall paint system

Formulation	Stormer viscosity,Initial (KU)	Stormer viscosity,overnight (KU)
RHEOLATE 150 (0.5% wt)	100	105
ASE (1.0% wt)	100	110

较少的添加量
优异储存稳定性

DEUCHEM
SOLVENTES & RESINS
海名斯·德康
2009/12

ELEMENTIS
SOLVATIVES

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® HASE thickeners

RHEOLATE 425

- > 30% active matter 30% 疏水改性丙烯酸碱溶胀型增稠剂
- > APE and VOC Free 环保型, 不含APE 和VOC,
- > Low odor 低气味
- > To provide excellent Stormer KU viscosity and ICI viscosity build. 提供良好的Stormer 粘度及ICI 粘度
- > Reduces spattering during roller application 优异的抗飞溅性能
- > Provides good balance of sag control and leveling 在抗流挂与流平之间保持良好的平衡
- > Excellent color development. 优异的展色性
- > Reduces syneresis. 降低分水现象
- > Recommended for medium PVC emulsion paint system 适用于中PVC建筑涂料

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® 425

Early Blistering Resistance Test
早期耐水起泡性测试

2009/1/12

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® 425

Better Leveling
更佳的流平性-

RHEOLATE 425 HEC

抗分水-更优异的热储存稳定性
(2周后, 50度热储)

HEC RHEOLATE 425

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® 425

Spatter Resistance 优异的抗飞溅性能

HEC RHEOLATE 425

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® 425

Flow 动态曲线-

HEC RHEOLATE 425

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® 425

45% PVC NO-VOC 内墙涂料体系

Stormer viscosity,KU,in 45% PVC NO-VOC Interior Wall Paint System

Product	Stormer viscosity, KU (Blue)	Stormer viscosity, KU (Red)	Stormer viscosity, KU (Yellow)
RHEOLATE 420	~100	~100	~100
RHEOLATE 425	~100	~100	~100
RHEOLATE 450	~90	~90	~90
Competitor 1	~80	~80	~80
Competitor 2	~100	~100	~100
Duopheno Wr-116	~100	~100	~100

EcoVAE TM 1608
Loading: 0.75%wt

DEUCHEM
德名斯·德康
2009/1/12

One-stop Total Solution Provider
一站式整体解决方案的伙伴

RHEOLATE® 425

ELEMENTIS
ASSOCIATIVES

45% PVC NO-VOC 内墙涂料体系

Color Development 展色性比较-碳黑色浆

RHEOLATE 425 取得最佳的展色性能

色浆添加量: 2%wt

DEUCHEM
海名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

RHEOLATE® 425

ELEMENTIS
ASSOCIATIVES

45% PVC NO-VOC 内墙涂料体系

Color Development 展色性比较-铁红色浆

RHEOLATE 425 取得最佳的展色性能

色浆添加量: 5%wt

DEUCHEM
海名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

Polyurethane Associative Thickeners /PEUPU缔合型增稠剂

ELEMENTIS
ASSOCIATIVES

DEUCHEM
海名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

ELEMENTIS
ASSOCIATIVES

环保型PEUPU缔合型流变助剂

不含 APE

不含 VOC

不含 锡

DEUCHEM
海名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

环保型PEUPU缔合型流变助剂

ELEMENTIS
ASSOCIATIVES

不含APE, VOC 和 锡

RHEOLATE® 644 - 25%固含, 提供较高剪切粘度

RHEOLATE® 678 - 25%固含, 提供中高剪切粘度

RHEOLATE® 655 - 20%固含, 提供中剪切粘度

RHEOLATE® 666 - 20%固含, 提供中低剪切粘度,
适合于喷涂体系


RHEOLATE® 212 - 20%, 提供牛顿型流动状态 / 高剪切粘度



聚氨酯缔合型增稠剂

DEUCHEM
海名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12





NO-VOC 内墙涂料体系

ELEMENTIS
ELEMENTIS

推荐于NO-VOC净味型涂料中——

- **RHEOLATE® 212**
提供牛顿性流体，同时提供最佳的展色性能
- **RHEOLATE® 644**
获得良好的斯托默粘度与ICI粘度，优异的展色性能
- **RHEOLATE® 678**
在较低的添加量时，获得较高的斯托默粘度和较高的ICI粘度，同时提供优异的展色性能

One-stop Total Solution Provider
一站式整体解决方案的伙伴

DEUCHEM
德名斯·德康
2009/1/12



DAPRO® DF 7000 系列

ELEMENTIS
ELEMENTIS

采取独特的生产技术

One-stop Total Solution Provider
一站式整体解决方案的伙伴

DEUCHEM
德名斯·德康
2009/1/12

DAPRO® DF 7000 系列

ELEMENTIS
ELEMENTIS
SPECIALISTE

超稳定型，不含 APE 及 VOC

DAPRO DF 7010

- 矿物油/蜡/有机硅
- 各种 PVC 系统
- 优异的稳定性
- 极佳的消泡抑泡性
- 良好的成本效益
- 较少的漆膜缺陷

DAPRO DF 7015

- 矿物油/蜡/有机硅
- 中、低 PVC 系统
- 优异的稳定性
- 极佳的消泡抑泡性
- 乳化型，易分散，适合后添加
- 适合于色浆、研磨浆系统，优异的耐热稳定性

DEUCHEM
德名斯·德康


One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

DAPRO DF7000系列评估

ELEMENTIS
ELEMENTIS
SPECIALISTE

鼓泡法-PA237纯丙乳液体系
---消泡剂添加量：0.3%



DEUCHEM
德名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴


2009/1/12

DAPRO® DF 7000 系列

ELEMENTIS
ELEMENTIS
SPECIALISTE

Loading: 0.3%wt

Defoaming test, in 30% PVC latex paint system
based on 296D



DEUCHEM
德名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴


2009/1/12

DAPRO® DF 7000 系列

ELEMENTIS
ELEMENTIS
SPECIALISTE

Loading: 0.3%wt

Defoaming test,in 75% PVC Latex Paint system
Based on BATF 998A



DEUCHEM
德名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

DAPRO® DF 7000 系列


ELEMENTIS
ELEMENTIS
SPECIALISTE

弹性拉毛体系的抑泡效果

DAPRO DF 7010



CONTROL



DEUCHEM
德名斯·德康


One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12

50% PVC NO-VOC内墙涂料体系

ELEMENTIS
ELEMENTIS
SPECIALISTE

DAPRO DF 7000 series defoamers in
low voc 50% interior wall paint system ,0.3% by wt
- Celvitol 1608 -Celanese



DEUCHEM
德名斯·德康

One-stop Total Solution Provider
一站式整体解决方案的伙伴

2009/1/12



Summary/小结



NUOSPERSE FN 265 -环保型非离子型润湿剂
NUOSPERSE FX605 -环保型聚丙烯酸钠盐分散剂
DAPRO DF 7010/7015 -超稳定型消泡剂
RHEOLATE 212/644/678 -环保型聚氨酯缩合型增稠剂
RHEOLATE 150/425 -环保型丙烯酸碱溶胀型增稠剂
BENAQUA 4000 -改性锂蒙脱石, 适合于厚浆型涂料
BENTONE DE -易分散型锂蒙脱石, 适合于水性金属涂料



One-stop Total Solution Provider
一站式解决方案提供商

Thank You !!

www.elementis-specialties.com

Walee Wang (Mr.)/ 王全义
Technical service manager

Walee.Wang@elementis.com
Mobile : 13816116438

Disclaimer
DEUCHEM information is, to the best of our knowledge, true and accurate. We advise the conditions of use and the safe use of our products. No warranty is given or to be implied in respect of such information. In every case, caution must be exercised to avoid violation or infringement of statutory obligations and/or any rights belonging to a third party. We are, at all time, willing to study customers' specific outlets involving our products in order to enable their most effective use.

2009/1/12

Information and Samples



For more information on Elementis Specialties products, please contact:

EUROPE

Elementis Specialties
De Kleeflaan 12A, bus 3
1831 Diegem, Belgium
sofie.raemdonck@elementis-eu.com
Tel: +32.2.790.7600
Fax: +32.2.790.7660

REST OF ASIA

Elementis Specialties, Inc.
Lot PT 55, 54 & 65, Jalan Hulu Tinggi 26/6,
Section 26, 40400 Shah Alam,
Selangor Darul Ehsan, Malaysia
Tel: +603.5191 9979
Fax: +603.5191 6811

AMERICAS

Elementis Specialties, Inc.
PO Box 700, 329 Wyckoffs Mill Road
Hightstown, New Jersey 08520, USA
della.adams@elementis-na.com
Tel: +1.609.443.2505
Fax: +1.609.443.2422

CHINA

Elementis Specialties, Inc.
99 Liangyang Road
Songjiang Industrial Zone
Shanghai 201413 China
Tel: +86.21.5774 0348
Fax: +86.21.5774 5356

www.elementis-specialties.com

Disclaimer

DEUCHEM information is, to the best of our knowledge, true and accurate, but since the conditions of use are beyond our control, no warranty is given or to be implied in respect of such information. In every case, caution must be exercised to avoid violation or infringement of statutory obligations and/or any rights belonging to a third party. We are, at all time, willing to study customers' specific outlets involving our products in order to enable their most effective use.

一站式解决方案提供商

2009/1/12